

Built-in and induced polarization across $\text{LaAlO}_3/\text{SrTiO}_3$ heterojunctions

Guneeta Singh-Bhalla,^{1,2,3,4,*} Christopher Bell,^{3,5} Jayakanth Ravichandran,⁶ Wolter Siemons,¹ Yasuyuki Hikita,³ Sayeef Salahuddin,⁷ Arthur F. Hebard,⁴ Harold Y. Hwang,^{3,5} and Ramamoorthy Ramesh^{1,2}

¹*Department of Physics, University of California, Berkeley, California 94720, USA*

²*Materials Science Division, Lawrence Berkeley National Laboratory, Berkeley, California 94720, USA*

³*Department of Advanced Materials Science, University of Tokyo, Kashiwa, Chiba 277, Japan*

⁴*Department of Physics, University of Florida, Gainesville, Florida 32611, USA*

⁵*Japan Science and Technology Agency, Kawaguchi, 332-0012, Japan*

⁶*Applied Science and Technology Graduate Group, University of California, Berkeley, California 94720, USA*

⁷*Department of Electrical Engineering and Computer Science, University of California, Berkeley, California 94720, USA*

(Dated: May 25, 2010)

Ionic crystals terminated at oppositely charged polar surfaces are inherently unstable and expected to undergo surface reconstructions to maintain electrostatic stability. Essentially, an electric field that arises between oppositely charged atomic planes gives rise to a built-in potential that diverges with thickness. In ultra thin film form however the polar crystals are expected to remain stable without necessitating surface reconstructions, yet the built-in potential has eluded observation. Here we present evidence of a built-in potential across polar LaAlO_3 thin films grown on SrTiO_3 substrates, a system well known for the electron gas that forms at the interface. By performing electron tunneling measurements between the electron gas and a metallic gate on LaAlO_3 we measure a built-in electric field across LaAlO_3 of 93 meV/Å. Additionally, capacitance measurements reveal the presence of an induced dipole moment near the interface in SrTiO_3 , illuminating a unique property of SrTiO_3 substrates. We foresee use of the ionic built-in potential as an additional tuning parameter in both existing and novel device architectures, especially as atomic control of oxide interfaces gains widespread momentum.

The creation of oxide thin films with polar surfaces has only recently become possible with the advent of termination control on SrTiO_3 (001) substrates.^{1,2} LaAlO_3 thin films grown on singly terminated SrTiO_3 surfaces comprise negatively charged AlO_2 and positively charged LaO end planes and are expected to be polar in the ionic limit.³⁻⁵ When at least four unit cells (u.c.) of LaAlO_3 are deposited on TiO_2 terminated SrTiO_3 , an electron gas forms near the interface in SrTiO_3 .⁶⁻⁸ It is often hypothesized that at the critical thickness of four u.c. the potential across LaAlO_3 exceeds the band gap of SrTiO_3 and electrons tunnel from the valence band of LaAlO_3 to the SrTiO_3 potential well, completely diminishing the potential across LaAlO_3 .⁹ Thus within this picture, in the presence of an electron gas no field would be expected across the LaAlO_3 . However, if all the charge carriers do not lie precisely at the interface or have an extrinsic (oxygen vacancies¹⁰ or cation doping¹¹) origin, the LaAlO_3 potential will not be fully screened and can thus be probed.¹² The precise band alignment between the LaAlO_3 and SrTiO_3 will also determine the strength of the residual fields in the LaAlO_3 .¹³ Addressing this issue and determining the existence of an uncompensated built-in potential in LaAlO_3 (or polar ionic insulators in general) is central to understanding surface reconstruction phenomenon in thin films.^{14,15}

We probe the potential landscape across the LaAlO_3 and the interface region in SrTiO_3 by employing a typical metal-insulator-metal capacitor geometry such that the LaAlO_3 thin films form the dielectric layer

sandwiched between evaporated metallic electrodes and the electron gas, as depicted in Fig. 1a and described in Methods. A bias voltage is applied to the top metallic electrode while the electron gas is held at ground.

A typical current-voltage (JV) curve measured between a Pt top electrode and the electron gas for an LaAlO_3 thickness, d_{LAO} , of 20 u.c. is shown in Fig. 1b and overlaid with theoretical curves, as labeled. Similar rectifying JV curves were measured for nine different LaAlO_3 films with d_{LAO} ranging from 5 to 40 u.c. Junctions thinner than $d_{\text{LAO}} = 20$ u.c. are well described by direct tunneling between the metal electrode and electron gas for both positive (+V) and negative (−V) applied biases, as described in detail in Supplementary Section I (SSI). Figure 1b shows excellent agreement to the theoretically calculated curve (black) for direct tunneling for +V. For samples with $d_{\text{LAO}} \geq 20$ u.c. however, an additional contribution from Zener tunneling for negative applied bias must be included, as shown in Fig. 1b.

The inset in Fig. 1c shows a sampling of the JV curves for various d_{LAO} with emphasis on the negative bias region at 100 K. It is clear that for a given voltage the current does not decrease monotonically with d_{LAO} . The main panel of Fig. 1c shows J as a function of d_{LAO} (open circles) at $V = -0.1$ V for all samples, revealing a clear peak at 20 u.c. (7.56 nm). The same trend is observed at all temperatures at negative bias. The dark blue curve in Fig. 1c shows calculated values for J vs. d_{LAO} within the direct tunneling model (see SSI), which also agrees well with the data for thicknesses below 20 u.c..

The sudden increase of tunneling current at $d_{\text{LAO}} = 20$ u.c. seen in Fig. 1c can be understood by considering the polar nature of LaAlO_3 . We recall that in the presence of a large enough electric field, Zener breakdown occurs in insulators and electrons tunnel from the valence to conduction band.¹⁶ For materials with a built-in polar field, the internal potential grows with increasing thickness until it equals the bandgap at a critical thickness, d^{cr} , giving rise to a significant increase in tunneling current.¹⁷ For LaAlO_3 thin films deposited on TiO_2 terminated SrTiO_3 , in the absence of complete screening an ionic built-in potential normal to the interface, pointing away from the SrTiO_3 is expected.^{5,9} Neglecting effects of the Pt electrode, Figs. 2a and 2b illustrate zero bias band diagrams (black outline) where the band bending in LaAlO_3 reflects the unscreened potential.^{5,13,14} In green, we also sketch the cases for positive (+V, Fig. 2a) and negative (-V, Fig. 2b) applied bias. When a metal film is brought into contact with LaAlO_3 the built-in potential may be further modified depending on the precise band alignments which are difficult to accurately predict in the presence of electronic reconstruction.¹³

The band diagram shown in Fig. 2a reflects the tunneling of electrons from the SrTiO_3 to the Pt electrode (not shown for simplicity). At large enough bias, electrons tunnel to the empty LaAlO_3 conduction band (Fowler-Nordheim tunneling¹⁸) for applied bias V , when $qV \geq qV_{bi} + \Delta E_C$, where V_{bi} is the net built-in potential across LaAlO_3 including contributions from both the ionic built-in potential *and* contributions from the metal work function. ΔE_C is the conduction band offset between the SrTiO_3 potential well and LaAlO_3 .

Figure 2b shows electrons tunneling from the metal into the SrTiO_3 well, as determined from the data shown in Fig. 1b. Above a critical LaAlO_3 thickness, d_{LAO}^{cr} , we also expect electron tunneling across the LaAlO_3 bandgap, via the valence states for applied bias V when:

$$qV \geq E_{g(\text{LAO})} - qV_{bi}. \quad (1)$$

Here $E_{g(\text{LAO})}$ is the bandgap of LaAlO_3 . Using the diagram in Fig. 2b, the current density of electrons tunneling across the LaAlO_3 bandgap was calculated within the WKB approximation^{16,17} as shown in SSI, using

$$\Phi(x) = E_{g(\text{LAO})} - qE_{bi}d_{\text{LAO}} - qV + \epsilon \quad (2)$$

as the potential barrier height, where ϵ is the total kinetic energy of the tunneling electrons, E_{bi} the effective built-in electric field in LaAlO_3 , and $V = -0.1$ V. We obtain the light blue curve shown in Fig. 1c, which is in excellent agreement with the data using the experimentally measured $E_{g(\text{LAO})} = 6.5$ eV¹⁹ for LaAlO_3 grown on SrTiO_3 .

A distinguishing feature of polar tunnel barriers is the low tunnel probability just below d^{cr} .¹⁷ Our measurements (Fig. 2c) indicate that d_{LAO}^{cr} lies somewhere between 17 u.c. and 20 u.c., or 18.5 ± 1.5 u.c. when using

Pt electrodes. Thus, using $d_{\text{LAO}}^{cr} = 18.5$, $a = 0.378$ nm²⁰ for the lattice constant of LaAlO_3 , and $E_{bi}d_{\text{LAO}}^{cr}a = qV_{bi} = E_{g(\text{LAO})} = 6.5$ eV (from Eq. 1 with $qV = 0$), we obtain $E_{bi} = 93.0$ meV/Å as an estimate for the built-in electric field across LaAlO_3 . E_{bi} reduces to 50.3 meV if tunneling from the LaAlO_3 valence to the SrTiO_3 conduction band is assumed instead, as discussed in SSI as an alternate scenario. Alternatively $E_{bi} = 80.1$ meV/Å if the bulk value, $E_{g(\text{LAO})} = 5.6$ eV is used instead. A thorough metal work-function dependence is needed to accurately determine the ionic built-in potential contribution to V_{bi} . We note that band bending in the LaAlO_3 from the metal alone cannot account for the observed thickness dependence. Although, we expect band bending from the Pt electrode to modify the measured V_{bi} , it is not clear what fraction of the ionic potential is partially screened by the electron gas or partially compensated by covalency within the LaAlO_3 .^{9,14}

It is interesting to note that $d_{\text{LAO}}^{cr} \approx 18.5$ u.c. for tunnel-coupling of the two LaAlO_3 surfaces (in the presence of a Pt electrode) is close to the value of 15 u.c. (using no metal electrode) above which a drop in the in-plane mobility²¹ and change in the in-plane magnetoresistance^{21,22} have previously been observed. Any hole gas present in the LaAlO_3 valence band for $d_{\text{LAO}} \geq d_{\text{LAO}}^{cr}$ will contribute to the measured hall resistance and calculated mobility (since contacts made to the SrTiO_3 gas are connected through the LaAlO_3 film), while the cross-over from positive to negative magnetoresistance for $d_{\text{LAO}} \geq d_{\text{LAO}}^{cr}$ may reflect bilayer effects similar to those observed in tunnel-coupled quantum wells.²³

Our data clearly reveal that the electron gas does not fully screen the ionic built-in potential across LaAlO_3 . This suggests a couple of possibilities: (i) the charge carriers do not all lie exactly at the interface and are buried one or a few monolayers within the SrTiO_3 , or (ii) the metal electrodes deposited on the LaAlO_3 modify the band alignments and thus the carrier density of the electron gas. The latter effect may explain the failure to detect a built-in potential using photoemission experiments conducted in the absence of metal electrodes.^{8,13} Although the present work cannot distinguish between the above scenarios, to the best of our knowledge uncompensated built-in electric fields across ionic insulators with polar terminations have not previously been detected.^{4,13} The resulting potential is analogous to the built-in potential that arises in semiconductors due to free charge separation and the switchable built-in potential found in ferroelectrics, generally resulting from covalently bonded dipoles. The ionic built-in potential is most similar to the potential found in piezoelectric materials which also results from covalent bonds and is tuneable. However, unlike the piezoelectric/ferroelectric potential, the ionic built-in potential is unique in that it results from permanent dipoles.

In addition to revealing a built-in potential across LaAlO_3 , the tunneling data also reveal information about the band profile in the SrTiO_3 potential well region.

The SrTiO₃ interface region can be probed by tuning both the charge density and the SrTiO₃ dielectric permittivity, χ_{STO} , with temperature and applied electric fields.^{10,24,25} If the LaAlO₃/SrTiO₃ heterostructure is compared to the inversion layer in a lightly doped metal-oxide-semiconductor (MOS) capacitor, we can expect changes in the charge density of the inversion layer as a function of temperature and gate voltage.²⁶ Changes in either of these quantities will be reflected in the barrier height, Φ for electrons tunneling *from* the SrTiO₃ potential well.

In order to probe changes in the barrier height, we tune χ_{STO} and the charge density using both temperature and an applied field across SrTiO₃, and measure the resulting tunneling curves as shown in Figs. 3a and 3c. In agreement with the discussion above, we find that in the $-V$ region where electrons are tunneling from the metal electrode via the LaAlO₃ valence band *to* the SrTiO₃ potential well, JV undergoes little change while significant changes are observed for electrons tunneling from the electron gas in SrTiO₃ for $+V$.

Both the backgate and temperature dependence data are qualitatively in agreement with the simple barrier height change arguments presented above. Fig. 3a shows JV curves for the 20 u.c. sample at several temperatures, while Fig. 3b shows changes in Φ as a function of temperature as obtained by fitting to the direct tunneling model (SS1). As fewer states are occupied in the interface region with decreasing temperature, the barrier height of electrons tunneling from the SrTiO₃ increases. Similarly, Fig. 3c shows JV for the 30 u.c. sample at 50 K for several back gate fields (E_{bg}) applied with respect to the electron gas, as schematically depicted in the inset. Fig. 3d shows the corresponding changes in Φ . This is in agreement with previous observations²⁵ where negative E_{bg} compresses the electron gas while also reducing the charge density. We do not observe significant changes in the Φ for positive E_{bg} . This is expected as the electron gas has a higher charge density and occupies a larger volume.²⁵ Interestingly, the change in Φ begins to level off below about 50 K in Fig. 3b. Since SrTiO₃ is an incipient ferroelectric and is sensitive to the slightest strain perturbation, it is possible that we are observing the effects of an interface dipole emerging at low temperatures.²⁷ A change in the dipole strength at the interface with temperature and an applied back gate will modify ΔE_C which can also change Φ .

Capacitance measurements are an excellent tool for probing this latter notion. Fig. 4a shows CV measured between the metal electrode and electron gas at 10 K for a 30 u.c. sample. (Supplementary Section II, or SSII, provides details about the complex impedance analysis). The onset of Zener tunneling at negative biases coincides with a sharp drop in C , which is accompanied by a sharp drop in the complex phase angle: Figure 4b shows the phase angle, δ , of the complex impedance as a function of V at several temperatures. δ is calculated to be exactly 90° for a perfect capacitor, becoming less than 90° as the

dielectric becomes more conducting (SSII). As seen here, the drop off to zero in $\delta(V)$ coincides with the sharp drop in CV and the onset of Zener tunneling. During Zener tunneling charge carriers are introduced into the LaAlO₃ conduction band and LaAlO₃ is no longer a good dielectric, behaving more like a resistor. When $\delta = 90^\circ$ however, the system behaves like a metal-insulator-metal tunnel junction. For samples thinner than 20 u.c., while we do observe a typical MOS capacitor depletion capacitance at high enough negative bias, no corresponding drop in the complex phase angle is observed (SSII).

Figures 4b to 4d provide a closer examination of the hysteretic behavior that appears below 100 K in both the CV and $\delta(V)$.²⁵ We find that the memory window defined by the hysteresis remains constant at $\Delta V = 0.16$ V for frequencies below the RC roll off when $V_{max} = 0.8$ V (Fig. 4b), and increases with decreasing temperature (Fig. 4c). The memory window also increases with increasing maximum applied voltage (V_{max} in Fig. 4d). The lack of a frequency dependence and decrease in hysteresis with increasing temperature rule out the role of interface traps which are more active at higher temperatures and have a characteristic time dependence associated with charging/discharging.²⁶

The data however compare well to the response measured for metal-ferroelectric-insulator-metal or semiconductor (MFIM or MFIS) junctions.^{28,29} Using the change in charge density for the high and low C values shown in Fig. 4a, we obtain 18 nC/cm² as an estimate of the remnant polarization for a maximum applied voltage of 0.8 V. Since ferroelectric behavior in LaAlO₃ has never been observed or expected, any dipole switching can be attributed to a thin layer in SrTiO₃ near the interface.³⁰ This also suggests that the electron gas lies not exactly at the interface, but buried one or a few monolayers within the SrTiO₃. It can thus be argued that the large influx of charge carriers into the potential well at the onset of Zener tunneling changes the local electric field and modifies the dipole strength.

These observations support recent experimental evidence of an induced polarization with bound charges in addition to free charge near the interface in SrTiO₃.^{31,32} Furthermore, there is evidence from both X-Ray³³ and TEM²⁰ measurements that when LaAlO₃ with a 3% lattice mismatch is deposited on the (001) SrTiO₃ substrates, distortions in the TiO₆ octahedra occur at the interface. It is also well known that biaxial strain as well as a strain gradient can induce ferroelectric³⁴ and flexoelectric³⁵ polarizations in SrTiO₃. The resulting bound charges would give rise to a finite electric field and confining potential at the interface.³⁶⁻³⁸ This is analogous to the mechanism that gives rise to a confined electron gas in wide band gap GaN based heterostructures.³⁹

Thus, in addition to polar LaAlO₃, the weak polarity of the SrTiO₃ appears to play an important role in determining the electrostatic boundary conditions at the LaAlO₃/SrTiO₃ interface. Theoretically, it was shown that depending on the termination layer, TiO₂ or SrO,

(001) bulk SrTiO₃, which is ionic-covalent and weakly polar, is expected to undergo weak electronic or structural reconstructions near the surface to avoid a diverging potential.⁴⁰ Very recently, it was shown that when polar LaAlO₃ overlayers are added to polar SrTiO₃, the accumulation of screening charges is one means for ensuring conservation of the electric displacement vector across the LaAlO₃/SrTiO₃ interface.⁴¹

To summarize, using capacitance and electron tunneling measurements we have provided experimental evidence of a finite built-in electric field across polar LaAlO₃. We have also shown evidence of a finite polarization and bound charge within SrTiO₃, highlighting a unique property of this oxide substrate. These two results provide key insights to understand and design novel interfaces in a controlled manner. Furthermore, built-in fields in large band gap polar insulators could potentially be exploited for applications such as reducing leakage current in transistors,⁴² achieving high power MOS capacitors and electron hole separation for enhancing built-in fields in pn junction diodes,¹⁷ etc. Essentially, a built-in field in singly terminated polar ionic insulators results from permanent dipoles while for non-polar doped semiconductors physical separation of positive and negative free charge carriers gives the same effect. As semiconductor device concepts achieve maturity, much of the same phenomenology can be translated to the complex oxides which offer many more degrees of freedom for exploration with applications perhaps not yet conceived.

Methods

The LaAlO₃/SrTiO₃ samples were fabricated by epitaxially depositing LaAlO₃ films on TiO₂ terminated

(001) SrTiO₃ substrates by pulsed laser deposition using a KrF laser. Before growth, the substrates were preannealed at 1223 K for 30 min in an oxygen environment of 0.67 mPa. Following this anneal the growth was performed at 1073 K in an oxygen pressure of 1.33 mPa, at a repetition rate of 2 Hz. The total laser energy was 20 mJ, and the laser was imaged to a rectangular spot of area approximately 2.3 x 1.3 mm² on the single crystal LaAlO₃ target using an afocal zoom stage. After growth, the samples were cooled to room temperature in an O₂ pressure of 4 × 10⁴ Pa, with a one hour pause at 873 K.^{7,25} Nine samples with LaAlO₃ thicknesses of 5, 7, 10, 13, 15, 17, 20, 30 and 40 u.c. were deposited in this way.

Several circular metallic electrodes with diameters ranging from 0.3 to 0.7 mm were thermally evaporated on each of the LaAlO₃ films using a shadow mask. Au was used for the 30 u.c. sample and Pt for all other samples. The backgate was thermally evaporated onto the 30 u.c. sample. Gold wire (0.0025" gauge) was manually bonded to the electrodes using silver epoxy and an Al wirebonder was used to bond to the electron gas. The samples were cooled in Quantum Design PPMS and MPMS systems. Tunneling measurements were conducted in Kashiwa, Gainesville and Berkeley, using various electrometers and source-measure units, all giving the same results. Capacitance measurements were also performed in all three locations using an HP 4284 LCR meter. For the back gate measurements, electric fields were applied in the following succession: 0 kV/cm → negative fields → positive fields.

* Corresponding author: guneeta@berkeley.edu

¹ Kawasaki, M. *et al.* Atomic Control of the SrTiO₃ Crystal Surface. *Science* **266**, 1540–1542 (1994).

² Koster, G., Kropman, B. L., Rijnders, G. J. H. M., Blank, D. H. A. & Rogalla, H. Quasi-ideal strontium titanate crystal surfaces through formation of strontium hydroxide. *Applied Physics Letters* **73**, 2920–2922 (1998).

³ Tasker, P. W. The stability of ionic crystal surfaces. *J. Phys. C: Sol. Stat. Phys.* **12**, 4977–4984 (1979).

⁴ Goniakowski, J., Finocchi, F. & Noguera, C. Polarity of oxide surfaces and nanostructures. *Rep. Prog. Phys.* **71**, 016501 (2008).

⁵ Nakagawa, N., Hwang, H. Y. & Muller, D. A. Why some interfaces cannot be sharp. *Nature Mat.* **5**, 204–209 (2006).

⁶ Ohtomo, A. & Hwang, H. Y. A high-mobility electron gas at the LaAlO₃/SrTiO₃ heterointerface. *Nature* **427**, 423–426 (2004).

⁷ Thiel, S., Hammerl, G., Schmehl, A., Schneider, C. W. & Mannhart, J. Tunable Quasi-Two-Dimensional Electron Gases in Oxide Heterostructures. *Science* **313**, 1942–1945 (2006).

⁸ Segal, Y., Ngai, J. H., Reiner, J. W., Walker, F. J. & Ahn, C. H. X-ray photoemission studies of the metal-insulator transition in LaAlO₃/SrTiO₃ structures grown by molecular beam epitaxy. *Phys. Rev. B* **80**, 241107 (2009).

⁹ Pentcheva, R. & Pickett, W. E. Electronic phenomena at complex oxide interfaces: Insights from first principles. *J. Phys.: Condens. Mat.* **22**, 043001 (14pp) (2010).

¹⁰ Siemons, W. *et al.* Origin of charge density at LaAlO₃ on SrTiO₃ heterointerfaces: Possibility of intrinsic doping. *Phys. Rev. Lett.* **98**, 196802 (2007).

¹¹ Willmott, P. R. *et al.* Structural basis for the conducting interface between *laalo3* and *srtio3*. *Phys. Rev. Lett.* **99**, 155502 (2007).

¹² Li, Y., Phattalung, S. N., Limpijumnong, S. & Yu, J. Oxygen-vacancy-induced charge carrier in n-type interface of LaAlO₃ overlayer on SrTiO₃: Interface vs. bulk doping carrier (2009). arXiv:0912.4805v1.

¹³ Gu, X., Elfimov, I. S. & Sawatzky, G. A. The role of the band gaps in reconstruction of polar surfaces and interfaces (2009). arXiv:0911.4145v1.

¹⁴ Noguera, C. & Goniakowski, J. Polarity in oxide ultrathin

- films. *J. of Phys: Cond. Matt.* (2008).
- ¹⁵ Goniakowski, J., Noguera, C. & Giordano, L. Prediction of uncompensated polarity in ultrathin films. *Phys. Rev. Lett.* **98**, 205701 (2007).
 - ¹⁶ Zener, C. A theory of electrical breakdown of solid dielectrics. *Proc. Roy. Soc. A* **145**, 523–529 (1934).
 - ¹⁷ Simon, J. *et al.* Polarization-induced Zener tunnel junctions in wide-band-gap heterostructures. *Phys. Rev. Lett.* **103**, 026801 (2009).
 - ¹⁸ Fowler, R. H. & Nordheim, L. Electron emission in intense electric fields. *Proc. R. Soc. Lond. A* **119**, 173–181 (1928).
 - ¹⁹ Mi, Y. Y. *et al.* Epitaxial LaAlO₃ thin film on silicon: Structure and electronic properties. *Appl. Phys. Lett.* **90**, 181925 (2007).
 - ²⁰ Maurice, J.-L. *et al.* Electronic conductivity and structural distortion at the interface between insulators SrTiO₃ and LaAlO₃. *Phys. Stat. Sol. (a)* **203**, 2209–2214 (2006).
 - ²¹ Bell, C., Harashima, S., Hikita, Y. & Hwang, H. Y. Thickness dependence of the mobility at the LaAlO₃/SrTiO₃ interface. *Appl. Phys. Lett.* **94**, 222111 (2009).
 - ²² Brinkman, A. *et al.* Magnetic effects at the interface between non-magnetic oxides. *Nature Mater.* **427**, 493–496 (2007).
 - ²³ Ihn, T., Carmona, H., Main, P. C., Eaves, L. & Henini, M. Magnetic-field-induced resonant tunneling in parallel two-dimensional systems. *Phys. Rev. B* **54**, R2315–R2318 (1996).
 - ²⁴ Copie, O. *et al.* Towards two-dimensional metallic behavior at LaAlO₃/SrTiO₃ interfaces. *Phys. Rev. Lett.* **102**, 216804 (2009).
 - ²⁵ Bell, C. *et al.* Dominant mobility modulation by the electric field effect at the LaAlO₃/SrTiO₃ interface. *Phys. Rev. Lett.* **103**, 226802 (2009).
 - ²⁶ Sze, S. M. *Physics of Semiconductor Devices* (Wiley-Interscience, 2006), 3 edn.
 - ²⁷ Müller, K. A. & Burkard, H. SrTiO₃: An intrinsic quantum paraelectric below 4 K. *Phys. Rev. B* **19**, 3593–3602 (1979).
 - ²⁸ Liu, M., Kim, H. K. & Blachere, J. Lead–zirconate–titanate based metal/ferroelectric/insulator/semiconductor structure for nonvolatile memories. *J. Appl. Phys.* **91**, 5985–5996 (2002).
 - ²⁹ Miller, S. L. & McWhorter, P. J. Physics of the ferroelectric nonvolatile memory field effect transistor. *J. Appl. Phys.* **72**, 5999–6010 (1992).
 - ³⁰ Bickel, N., Schmidt, G., Heinz, K. & Müller, K. Ferroelectric relaxation of the SrTiO₃(100) surface. *Phys. Rev. Lett.* **62**, 2009–2011 (1989).
 - ³¹ Ogawa, N. *et al.* Enhanced lattice polarization in SrTiO₃/LaAlO₃ superlattices measured using optical second-harmonic generation. *Phys. Rev. B* **80**, 081106 (2009).
 - ³² Salluzzo, M. *et al.* Orbital reconstruction and the two-dimensional electron gas at the LaAlO₃/SrTiO₃ interface. *Phys. Rev. Lett.* **102**, 166804 (2009).
 - ³³ Vonk, V. *et al.* Interface structure of SrTiO₃/LaAlO₃ at elevated temperatures studied in situ by synchrotron X-rays. *Phys. Rev. B* **75**, 235417 (2007).
 - ³⁴ Haeni, J. H. *et al.* Room-temperature ferroelectricity in strained SrTiO₃. *Science* **430**, 758–761 (2004).
 - ³⁵ Zubko, P., Catalan, G., Buckley, A., Welche, P. R. L. & Scott, J. F. Strain-gradient-induced polarization in SrTiO₃ single crystals. *Phys. Rev. Lett.* **99**, 167601 (2007).
 - ³⁶ Pentcheva, R. & Pickett, W. E. Ionic relaxation contribution to the electronic reconstruction at the n-type LaAlO₃/SrTiO₃ interface. *Phys. Rev. B* **78**, 205106 (2008).
 - ³⁷ Yoshimatsu, K., Yasuhara, R., Kumigashira, H. & Oshima, M. Origin of metallic states at the heterointerface between the band insulators LaAlO₃ and SrTiO₃. *Phys. Rev. Lett.* **101**, 026802 (2008).
 - ³⁸ Glinchuk, M. D. & Morozovska, A. N. The internal electric field originating from the mismatch effect and its influence on ferroelectric thin film properties. *J. Phys.: Condens. Matter* **16**, 3517–3531 (2004).
 - ³⁹ Ambacher, O. *et al.* Two dimensional electron gases induced by spontaneous and piezoelectric polarization in undoped and doped AlGaIn/GaN heterostructures. *J. Appl. Phys.* **87**, 334–344 (2000).
 - ⁴⁰ Goniakowski, J. & Noguera, C. The concept of weak polarity: An application to the SrTiO₃ (001) surface. *Surf. Sci.* **365** (1996).
 - ⁴¹ Stengel, M. & Vanderbilt, D. Berry-phase theory of polar discontinuities at oxide-oxide interfaces. *Phys. Rev. B* **80**, 241103 (2009).
 - ⁴² Cao, Y., Zimmermann, T., Xing, H. & Jena, D. Polarization-engineered removal of buffer leakage for GaN transistors. *Appl. Phys. Lett.* **96**, 042102 (2010).

Acknowledgments

We thank M. Gajek and J. H. Bardarson at UC Berkeley for discussions. GSB acknowledges support from the Japan Society for Promotion of Science (Award No. SP08057) and the U.S. National Science Foundation (Award No. OISE0812816) under the 2008 EAPSI fellowship program. The work at Berkeley (RR) was supported by the US Department of Energy under contract No. DE-AC02-05CH1123. The work at Florida (AFH) was supported by the US National Science Foundation under Grant No. 0404962. WS acknowledges support from the Dutch Organization for Scientific Research (NWO-Rubicon Grant).

Author Contributions

CB deposited the LaAlO₃ films. GSB prepared and measured the tunnel junctions with CB, and modeled/analyzed the data with JR and WS. SS simulated the *JV* curves within the NEGF approach. The manuscript was prepared by GSB with assistance from CB, JR, WS and YH. HYH, AFH and GSB contributed to conceptualizing the experiment. HYH provided insights and expertise on the LaAlO₃/SrTiO₃ interface, RR on ferroelectricity and AFH on interpreting complex impedance.

Competing Financial Interests

The authors declare no competing financial interests.

Figure Legends

Figure 1

Built-in polarization across LaAlO₃/SrTiO₃ tunnel junction diodes | **a**, Tunnel junctions are formed between thermally evaporated circular metallic electrodes on LaAlO₃ and the electron gas, as described in Methods. **b**, JV curve measured at 10 K for a 20 u.c. sample compared to curves calculated within the direct and Zener tunneling models as labeled, and described in SSI. **c**, J vs. LaAlO₃ thickness, d_{LAO} , for all samples at $V = -0.1$ V showing a clear peak at 20 u.c. (7.56 nm). Calculated curves for direct tunneling (dark blue) and Zener tunneling (light blue) are labeled and shown. The inset provides a closer look at the negative bias region of JV for several thicknesses showing that J does not scale monotonically with thickness for a given V (see dotted line at $V = -0.1$ V).

Figure 2

Thickness dependent built-in potential and inter-band tunneling across polar LaAlO₃ | **a**, A schematic band diagram of the LaAlO₃/SrTiO₃ interface at zero bias (black outline) showing the onset of Fowler-Nordheim tunneling for positive applied bias ($+V$, green outline) and, **b**, the onset of Zener tunneling at negative applied bias ($-V$, green outline) at a critical thickness across polar LaAlO₃ with a built-in electric field.

Figure 3

Tuning the tunneling current across LaAlO₃ by tuning the SrTiO₃ permittivity and charge den-

sity | **a**, JV curves for a 20 u.c. LaAlO₃ sample are shown for several temperatures with theoretical fits to the direct tunneling model (black). The inset schematically depicts how changes in the Fermi level with temperature or applied back-gate fields (E_{F1} at 300 K and E_{F2} at 10 K) affect the charge density in the SrTiO₃ potential well region and hence the barrier height Φ . **b**, Barrier heights extracted from fits to the direct tunneling model for each of the JV curves shown in **a**. **c**, JV for a 30 u.c. LaAlO₃ at 50 K for several different positive and negative applied SrTiO₃ back-gate fields, E_{bg} . The effect is much more pronounced for negative rather than positive biases. **d**, Each of the JV curves shown in **c** was also fit to the direct tunneling model. The barrier height increases linearly with increasingly negative backgate fields.

Figure 4

Capacitance measurements agree with JV while also revealing an induced dipole in SrTiO₃ | **a**, CV curves for a 30 u.c. sample measured at 10 K and 10 kHz is qualitatively similar to a metal-insulator-semiconductor (MIS) capacitor curve with a ferroelectric contribution, or a metal-insulator-ferroelectric-semiconductor (MIFS) capacitor. The drop in CV occurs during the Zener tunneling regime when carriers are introduced into the LaAlO₃ conduction band, making it a leaky dielectric. **b**, The phase angle of the measured complex impedance as shown at several temperatures. A hysteresis appears near 100 K and increases with decreasing temperature. **c**, The hysteresis is frequency independent for frequencies below the RC roll-off limit, and **d**, the hysteresis window, ΔV , increases with the maximum applied voltage, V_{max} , for a given sweep. **b** to **d** together qualitatively provide strong indications of dipole switching at the interface in SrTiO₃.